

# Test Report



Verification Website: [www.gttctech.com](http://www.gttctech.com)

Verification Code: GECH-2286-54

Scan to download



No: 220385332

Issue Date: 2022-12-23

Applicant: SHANGHAI SHUOTE NONWOVENS CO., LTD  
Address: NO. 8399, TINGFENG ROAD, FENGJING INDUSTRIAL PARK, JINSHAN DISTRICT, SHANGHAI CHINA

Information confirmed by applicant:

Padding

Quantity: 1 piece

Colour: White

Model: FY-3

Weight: 180g

Manufacturer: SHANGHAI SHUOTE NONWOVENS CO., LTD

Basis of judgement:

Date Received/Date Test Started: 2022-12-16

Conclusion:

Warmth retention property

Note: "M"-Meet the standard's requirement "F"-Fail to meet the standard's requirement  
"---"-No comment

Remark:  
This report is the english translation version of the report 220385331.  
All the tested items are tested under the standard condition (except for indication).  
Copies of the report are valid only re-stamped.  
The experiment was carried out at No.1, Zhujiang Road, Panyu District, Guangzhou, Guangdong, P.R.China.

Approved By:  
ShaoJuan Chen Engineer


Shao Juan Chen





## Test Report

No: 220385332





# Test Report

No:220385332

Warmth retention property

(GB/T 35762-2017)

Clo 2.55

Thermal resistance ( $K \cdot m^2 / W$ ) 0.395

—End of Report—

